

## PROCESS FOR THE PRODUCTION OF BUILDING ELEMENTS USED FLY ASH

**Patent number:** KR9309663  
**Publication date:** 1993-10-08  
**Inventor:** CHOE JONG-UK (KR)  
**Applicant:** CHOE JONG UK (KR); KIM NAM KU (KR); SHIN BYONG CHAN (KR)  
**Classification:**  
**- International:** C04B18/06; C04B24/20; C04B14/28  
**- european:**  
**Application number:** KR19910012986 19910729  
**Priority number(s):** KR19910012986 19910729

### Abstract of **KR9309663**

The brick for building is produced by mixing 45-60 wt.% fly ash as aggregate source with 35-50 wt.% first chemical additive having of sodium silicate mixture and 2% cationic surfactant in the ratio of 1:2-3 at 60 rpm mixing speed changing direction of rotation at 1 minute intervals for 5-7 minutes, adding and mixing 5 wt.% second chemical additive solution having 20 % calcium dehydrate at 80 rpm mixing speed in the same way as above for 10 minutes, moulding, heating at the rate of 10 deg.C per 1 minute, curing at 250 deg.C for 10 hours, cooling at the same rate.

---

Data supplied from the **esp@cenet** database - Worldwide